

SKAPS GE-180
NON-WOVEN GEOTEXTILE



SKAPS INDUSTRIES

335 Athena Drive,
Athens, GA 30601
Ph: (706)-354-3700
Fax: (706)-354-3737
Email: contact@skaps.com

SKAPS GE-180 is a needle-punched nonwoven geotextile made of 100% virgin polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GE-180 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered alkalis and acids. Polypropylene is stable within the pH range of 2 to 13.

SKAPS GE-180 conforms to the Minimum Average Roll Values (MARV) listed below:

PROPERTY	TEST METHOD	ENGLISH (MARV ²)	METRIC (MARV ²)
Weight	ASTM D-5261	8 oz/yd ²	271 g/m ²
Grab Tensile Strength	ASTM D 4632	225 lbs	1 kN
Grab Elongation	ASTM D 4632	50%	50%
Trapezoid Tear Strength	ASTM D 4533	90 lbs	0.4 kN
Thickness ⁴	ASTM D-5199	100 mils	2.5 mm
CBR Puncture Resistance	ASTM D 6241	600 lbs	2.67 kN
Permittivity ⁴	ASTM D 4491	1.26 sec ⁻¹	1.26 sec ⁻¹
Permeability ⁴	ASTM D 4491	0.3 cm/sec	0.3 cm/sec
Water Flow ⁴	ASTM D 4491	100 gpm/ft ²	4074 l/min/m ²
Apparent Opening Size (AOS) ^{3&4}	ASTM D 4751	80 US Sieve	0.18 mm
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.

PACKAGING

Roll Dimensions (W x L)	15 ft. x 690 ft.	4.58 m x 210.31 m
Area Per Roll	1150 Yd ²	963 m ²
Estimated Roll Weight - lbs	620 lbs.	282 kg

NOTES:

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. Maximum Average Roll Value (MaxARV)
4. At time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.