

**SKAPS TRANSNET™**  
**HDPE GEOCOMPOSITE**  
**WITH TN 270 GEONET**



**SKAPS INDUSTRIES**

571 Industrial Pkwy,  
 Commerce, GA 30529  
 Phone: (706) 336-7000  
 Fax: (706) 336-7007  
 E-Mail: contact@skaps.com

SKAPS TRANSNET™ Geocomposite consists of SKAPS Geonet made from HDPE resin with nonwoven polypropylene geotextile fabric heat bonded on one side or both sides of Geonet.

PROPERTY	TEST METHOD	UNIT	VALUE		QUALIFIER
<b>GEONET</b>					
Thickness	ASTM D 5199	mm	6.35	6.35	MAV <sup>(3)</sup>
Carbon Black	ASTM D 4218	%	2.0	2.0	MAV
Tensile Strength	ASTM D 7179	N/mm	9.62	9.62	MAV
Melt Flow	ASTM D 1238 <sup>(2)</sup>	g/10 min	1.0	1.0	Maximum
Density	ASTM D 1505	g/cm <sup>3</sup>	0.94	0.94	MAV
Transmissivity <sup>(1)</sup>	ASTM D 4716	m <sup>2</sup> /sec	3.0 x 10 <sup>-3</sup>	3.0 x 10 <sup>-3</sup>	MAV
<b>GEOCOMPOSITE</b>			<b>200 g/m<sup>2</sup></b>	<b>270 g/m<sup>2</sup></b>	
Ply Adhesion	ASTM D 7005	g/cm	178	178	MAV
Transmissivity <sup>(1)</sup> DS	ASTM D 4716	m <sup>2</sup> /sec	<b>TN 270-2-6</b>	<b>TN 270-2-8</b>	
			5.0 x 10 <sup>-4</sup>	5.0 x 10 <sup>-4</sup>	MAV
Transmissivity <sup>(1)</sup> SS	ASTM D 4716	m <sup>2</sup> /sec	<b>TN 270-1-6</b>	<b>TN 270-1-8</b>	
			1.5 X 10 <sup>-3</sup>	1.5 X 10 <sup>-3</sup>	MAV
<b>GEOTEXTILE</b>					
Fabric Weight	ASTM D 5261	g/m <sup>2</sup>	200	270	MARV <sup>(4)</sup>
Grab Tensile	ASTM D 4632	N	711	1001	MARV
Grab Elongation	ASTM D 4632	%	50	50	MARV
Trapezoid Tear	ASTM D 4533	N	289	400	MARV
CBR Puncture	ASTM D 6241	N	2002	2670	MARV
Water Flow <sup>(5)</sup>	ASTM D 4491	l/min/m <sup>2</sup>	5093	4075	MARV
Permittivity <sup>(5)</sup>	ASTM D 4491	sec <sup>-1</sup>	1.63	1.26	MARV
Permeability <sup>(5)</sup>	ASTM D 4491	cm/sec	0.30	0.30	MARV
AOS	ASTM D 4751	mm	0.212	0.180	MaxARV

**Notes:**

- (1) Transmissivity measured using water at 21 ± 2 °C (70 ± 4 °F) with a gradient of 0.1 and a confining pressure of 479 kPa between steel plates after 15 minutes. Values may vary with individual labs.  
 DS - Double Sided, SS - Single Sided
- (2) Condition 190/2.16
- (3) Minimum average value.
- (4) MARV is statistically defined as mean minus two standard deviations and it is the value which is exceeded by 97.5% of all the test data.
- (5) At the time of manufacturing. Handling may change these properties.

*This information is provided for reference purposes only and is not intended as a warranty or guarantee.*

*SKAPS assumes no liability in connection with the use of this information. Geotextile and Geonet properties are prior to lamination.*