

SKAPS TRANSNET™
HDPE GEONET TN 220



SKAPS INDUSTRIES

571 Industrial Pkwy,
Commerce, GA 30529
Phone: (706) 336-7000
Fax: (706) 336-7007
E-Mail: contact@skaps.com

SKAPS TRANSNET™ geonet consists of SKAPS Geonet made from HDPE resin.

PROPERTY	TEST METHOD	UNIT	VALUE	QUALIFIER
Thickness	ASTM D 5199	mm	5.08	MAV ⁽³⁾
Carbon Black	ASTM D 4218	%	2.0	MAV
Tensile Strength	ASTM D 7179	N/mm	7.87	MAV
Melt Flow	ASTM D 1238 ⁽²⁾	g/10 min	1.0	Maximum
Density	ASTM D 1505	g/cm ³	0.94	MAV
Transmissivity ⁽¹⁾	ASTM D 4716	m ² /sec	2.0 x 10 ⁻³	MAV

Notes:

- (1) Transmissivity measured using water at 21 ± 2 °C (70 ± 4 °F) with a gradient of 0.1 and a confining pressure of 479 kPa between steel plates after 15 minutes. Values may vary with individual labs.
- (2) Condition 190/2.16
- (3) Minimum average value

*This information is provided for reference purposes only and is not intended as a warranty or guarantee.
SKAPS assumes no liability in connection with the use of this information.*