

SKAPS GT-116

CONCRETE BREAKER
NON-WOVEN GEOTEXTILE



SKAPS INDUSTRIES

335 Athena Drive,
Athens, GA 30601
Ph: (706)-354-3700
Fax: (706)-354-3737
Email: contact@skaps.com

SKAPS GT116 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GT116 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13.

SKAPS GT116 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	ENGLISH (MARV2)	METRIC (MARV ²)
Weight	ASTM D 5261	14.8 oz/yd ²	508 g/m ²
Wide Width Tensile	ISO 10319/ ASTM D 4595	685 Lb/ft	10 kN/m
Wide Width Elongation	ISO 10319/ ASTM D 4595	60%	60%
Thickness	ISO 9863-1	(a) at 2 kPa:120 mils (b) at 20 kPa :100 mils (c) at 200 kPa: 40 mils	(a) at 2 kPa: 3 mm (b) at 20 kPa :2.5 mm (c) at 200 kPa: 1 mm
Permeability under load	ASTM 5493	(a) at 20 kPa: 0.0001 m/s	(a) at 20 kPa: 0.0001 m/s
Hydraulic Conductivity	ASTM 6574	(a) at 20 kPa : 0.0005 m/s (b) at 200 kPa: 0.0002 m/s	(a) at 20 kPa : 0.0005 m/s (b) at 200 kPa: 0.0002 m/s
UV Resistance	ASTM D 4355	70%/500 hrs.	70%/500 hrs.
Color	Visual		Black

* At the time of manufacturing. Handling may change these properties.

PACKAGING

Roll Dimensions (W x L)	15 x 390 ft	4.58 x 119 m
Area Per Roll	650 yd ²	545 m ²
Estimated Roll Weight	620 lbs	281 kg

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.