

**NON-WOVEN GEOTEXTILES
FOR TRANSPORTATION APPLICATION**
COMPARATIVE PRODUCT SPECIFICATION CHART



SKAPS INDUSTRIES

335 Athena Drive,
Athens, GA 30601
Ph: (706)-354-3700
Fax: (706)-354-3737
Email: contact@skaps.com

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)										
			GT131	GT135	GT140	GT142	GT150	GT160	GT170	GT180	GT110	GT112	GT116
Grab Tensile	ASTM D 4632	lbs	80	90	100	120	135	160	180	205	250	300	380
		kN	0.355	0.401	0.445	0.533	0.600	0.711	0.800	0.911	1.112	1.334	1.690
Grab Elongation	ASTM D 4632	%	50	50	50	50	50	50	50	50	50	50	50
Trapezoid Tear Strength	ASTM D 4533	lbs	30	40	45	50	55	60	75	85	100	115	145
		kN	0.13	0.18	0.20	0.22	0.24	0.27	0.33	0.38	0.45	0.51	0.65
CBR Puncture Resistance	ASTM D 6241	lbs	175	265	300	340	350	410	475	535	700	850	1080
		kN	0.78	1.18	1.33	1.51	1.56	1.82	2.11	2.37	3.11	3.78	4.80
Permittivity*	ASTM D 4491	sec ⁻¹	2.2	2	2	1.7	1.6	1.5	1.4	1.4	1.2	1	0.7
Water Flow*	ASTM D 4491	gpm/ft ²	150	150	140	135	115	110	105	95	80	75	50
		l/min/m ²	6095	6095	5689	4885	4684	4480	4074	3657	3251	3055	2035
AOS*	ASTM D 4751	US Sieve	50	50	70	70	70	70	70	80	100	100	100
		mm	0.3	0.3	0.212	0.212	0.212	0.212	0.212	0.18	0.15	0.15	0.15
UV Resistance at 500 hrs	ASTM D 4355	%	70	70	70	70	70	70	70	70	70	70	70

* At the time of manufacturing. Handling may change these properties.

AASHTO CLASSIFICATION

M288 Survivability Class	-	-	-	3	3	2	2	1	1	1	1
M288 Application ⁺	-	-	S/F	S/F	S/F	SP,D	SP,D	SP,ST, D,E	SP,ST, D,E	SP,ST, D,E	SP,ST, D,E

+ S/F=Slit Fence, SP=Separation, ST=Stabilization, E=Erosion Control, D=Drainage

PACKAGING DETAILS

Roll Dimension	(ft)	12.5/15 x 360				12.5 x 360/15 x 300						15 x 150
	(m)	3.81 x 109.8 / 4.6 x 109.8				3.81 x 109.8 / 4.6 x 91.4						4.6 x 46
Area per Roll	(yd ²)	500/600				500						250
	(m ²)	418/505				418						210
Estimated Roll Weight	(lbs)	125/145	130/155	146/172	152/180	187	195	220	250	320	375	250
	(kg)	57/66	59/70	66/78	69/82	85	89	100	114	145	170	114

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.