

SKAPS M706
WOVEN GEOTEXTILE



SKAPS INDUSTRIES

335 Athena Drive,
Athens, GA 30601
Ph: (706)-354-3700
Fax: (706)-354-3737
Email: contact@skaps.com

SKAPS woven geotextile fabrics are woven polypropylene materials offering optimum performance when used in stabilization and drainage applications. Produced from first quality raw materials, they provide the perfect balance of strength and separation in styles capable of functioning exceptionally well in a wide range of performance requirements. SKAPS M706 resists ultraviolet resistance, rotting, biological degradation and it is chemically inert to any natural bases or acids.

Unless indicated below, all listed properties are Minimum Average Roll Values:

PROPERTY	TEST METHOD	ENGLISH (MARV ²)	METRIC (MARV ²)
Grab Tensile	ASTM D 4632	370 x 250 lbs	1.65 x 1.11 kN
Grab Elongation	ASTM D 4632	16% x 15%	16% x 15%
Trapezoidal Tear	ASTM D 4533	100 x 60 lbs	445 x 0.267 kN
CBR Puncture Resistance	ASTM D 6241	950 lbs	4.28 kN
Water Flow ³	ASTM D 4491	18 gpm/sf	733 l/min/sm
Permittivity ³	ASTM D 4491	0.28 Sec ⁻¹	0.28 Sec ⁻¹
AOS ³	ASTM D 4751	70 US Sieve	0.212 mm
UV Resistance	ASTM D 4355	90/500 %/hrs	90/500 %/hrs

PACKAGING

Roll Dimensions (W x L)	12.0 ft x 300 ft	3.66 m x 91 m
Area Per Roll	400 yd ²	346 m ²

NOTES:

1. The property values listed above are subject to change without notice.
2. Minimum Average Roll Values (MARV) is calculated as the average minus two standard deviations. Statistically, it yields approximately 97.5% degree of confidence that any samples taken from quality assurance testing will meet or exceed the values described above.
3. At time of manufacturing. Handling, storage and shipping may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.