



SKAPS Industries  
571 Industrial Parkway  
Commerce, GA 30529 (U.S.A.)  
Phone (706) 336-7000 Fax (706) 336-7007  
e-mail: [info@skaps.com](mailto:info@skaps.com)

**SKAPS TRANSNET™ (TN)  
HDPE GEONET 160**

SKAPS TRANSNET™ geonet consists of SKAPS GeoNet made from HDPE resin.

Property	Test Method	Unit	Required Value	Qualifier
<b>Geonet</b>				
Mass per Unit Area	ASTM D 5261	lb/ft <sup>2</sup>	0.12	Minimum
Thickness	ASTM D 5199	mil.	160±10	Range
Carbon Black	ASTM D 4218	%	2 to 3	Range
Tensile Strength	ASTM D 5035	lb/in	30	Minimum
Melt Flow	ASTM D 1238 <sup>3</sup>	g/10 min.	1	Maximum
Density	ASTM D 1505	g/cm <sup>3</sup>	0.94	Minimum
Transmissivity <sup>1</sup>	ASTM D 4716	m <sup>2</sup> /sec.	1x10 <sup>-3</sup>	MARV <sup>2</sup>

**Notes:**

1. Transmissivity measured using water at 21 ± 2°C (70 ± 4°F) with a gradient of 0.1 and a confining pressure of 10000 psf between stainless steel plates after 15 minutes. Values may vary between individual labs.
2. MARV is statistically defined as mean minus two standard deviations and it is the value which is exceeded by 97.5% of all the test data.
3. Condition 190/2.16

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.